

NQR of barium in BaBiO₃ and BaPbO₃

M. M. Savosta, V. D. Doroshev, V. A. Borodin, Yu. G. Pashkevich, V. I. Kamenev and T. N. Tarasenko
Donetsk Institute of Physics & Technics, National Academy of Sciences of Ukraine, 83114 Donetsk, Ukraine

J. Englich and J. Kohout

Faculty of Mathematics & Physics, Charles University, V. Holešovičkách 2, 180 00 Praha 8, Czech Republic

A. G. Soldatov, S. N. Barilo and S. V. Shiryayev

Institute of Physics of Solids & Semiconductors, Academy of Sciences, 220072 Minsk, Belarus

(February 1, 2008)

The NQR on Ba nuclei was studied in four samples of BaBiO₃ prepared in different ways and, in addition, in BaPbO₃. The spectrum of ¹³⁷Ba at $T = 4.2$ K consists of relatively broad line centered near 18 MHz for all BaBiO₃ samples and near 13 MHz for BaPbO₃. The integrated intensity of ¹³⁷Ba resonance in ceramic sample BaBiO₃ synthesized at 800°C is approximately two times larger than in ceramic samples and single crystal prepared at 930-1080°C. The decrease of the NQR signal can be attributed to the partial disordering of charge disproportionated Bi ions on the two inequivalent sites. The broadening of the resonance indicates that local distortions of crystal structure exist in both compounds. The point charge model was used to analyse the electric field gradient on the Ba sites.

71.45.Lr, 76.60.Gv, 61.72.Hh

I. INTRODUCTION

The valence state of Bi in BaBiO₃ has long been the matter of dispute. Two models invoked are the domination of the Bi⁴⁺ valency implied by the composition, and the charge disproportionation of Bi⁴⁺ ions into Bi³⁺ and Bi⁵⁺ (in the ionic limit) giving rise to commensurate charge-density waves. The latter model is based on the results of neutron diffraction which demonstrate that the Bi ions occupy two crystallographically inequivalent sites with significantly different Bi-O bond lengths [1–3]. These results are supported by EXAFS and optical studies [4,5]. On the other hand, band structure calculations [6] and defect simulation studies [7], supported by the results of x-ray photoemission [8] and x-ray absorption near-edge structure spectroscopy [9], point to a minimal charge transfer between the two Bi sites.

Using the neutron diffraction technique, Chaillout *et al.* [10] found two types of crystal structure in BaBiO₃ samples prepared in different ways. The samples prepared or subsequently heat-treated at 800°C (group I) are characterized by significant differences between two average Bi-O distance whereas the samples synthesized from the melt ($T = 1125^\circ\text{C}$, group II) are characterized by negligible differences. The DTA measurements revealed an additional phase transition at 860°C on heating and 801°C on cooling in BaBiO₃. Chaillout *et al.* proposed that this transition probably corresponds to the disproportionation of the Bi into Bi³⁺ and Bi⁵⁺ cations and that below 800°C two structure arrangements of Bi ions exist. The first is characterized by a partial (75%) order of the Bi³⁺ and Bi⁵⁺ cations on the two inequivalent sites (group I) while the second structure corresponds to

a total disorder of Bi³⁺ and Bi⁵⁺ cations (group II).

Nuclear quadrupole resonance (NQR) can provide further insight in the valence state of Bi because it probes locally a distribution of electric field gradients (EFG) at the lattice sites. However, up to now only ¹⁷O NMR studies [11] have been performed. In the present paper we report the first observation of the ^{135/137}Ba NQR in BaBiO₃. The results for the samples which belong to group I and group II in a classification of Chaillout *et al.* are presented. For comparison the NQR of Ba in BaPbO₃ compound was also measured.

II. SAMPLE PREPARATION AND CHARACTERIZATION

Powder samples of BaBiO₃ were prepared by solid-state reaction in air. For the sample 1 the starting materials BaCO₃ and Bi₂O₃ were mixed carefully and treated at 800°C for 8 h. After grinding and pressing to bars the sample was annealed at 800°C for 30 h. For the sample 2 the mixtures were first fired for 11 h with three intermediate grindings and pressings. The temperature of firing was systematically increased from 800°C to 950°C. The powder was then melted at 1080°C and quenched to room temperature afterwards. Finally, sample 2 was quickly heated to 930°C and slowly (1.7°h^{-1}) cooled to achieve the oxygen stoichiometry. Sample 3 was obtained in the same way as sample 2 but without melting. Single crystal of BaBiO₃ (sample 4) was prepared by melting at 1080°C a mixture of BaCO₃ and Bi₂O₃, enriched with respect to Ba (2 at.%).

Powder sample of BaPbO₃ was prepared by firing ap-

propriate mixtures of BaCO_3 and PbO at 850°C for 18 h in air. After grinding and pressing to bars the sample was annealed at 950°C for 25 h.




FIG. 1. X-ray powder diffraction patterns around the (420) cubic reflection ($\text{Ni K}\alpha$ radiation) in different BaBiO_3 samples prepared as described in the text. Dashed curve corresponds to the pattern for sample 1 after it was annealed at 950°C for 6h.

To characterize the samples, x-ray powder diffraction measurements using filtered $\text{Ni K}\alpha$ radiation in the 2θ range 10 – 150° were performed at room temperature. All compounds were found to be single phase and no traces of starting materials were observed in the diffraction patterns. In accordance with early reports [1–3] the crystal structure of BaBiO_3 samples was found to be monoclinic, space group $I2/m$.

TABLE I. Lattice parameters for BaBiO_3 samples

No	$T_{\text{prep}} (^\circ\text{C})$	$a (\text{\AA})$	$b (\text{\AA})$	$c (\text{\AA})$	β
1	800	6.182(2)	6.136(3)	8.663(3)	90.17(3)
2	1080	6.187(2)	6.143(4)	8.673(4)	90.14(4)
3	930	6.183(3)	6.137(4)	8.662(4)	90.15(5)
4	1080	6.184(2)	6.136(3)	8.670(3)	90.14(3)

The unit cell parameters were determined from the splitting of the high-angle lines, corresponding to cubic (420), (332) and (442) reflections. The results are listed in Table I. The lattice parameters agree well with those reported in the literature [1–3,10]. Note that it was found in Ref. 10 that the monoclinic angle β is larger for the samples sintered at 800°C than the angle for samples sintered at 1125°C . This tendency may also be seen in Table I, though for our data the difference is in the limit of the experimental error.

It is interesting to note that in the present x-ray studies we found that the width of the diffraction peaks is similar in samples 2–4, while it is substantially narrower in sample 1. Shown in Fig. 1 is the diffraction pattern corresponding to the (420) cubic reflection for polycrystalline samples under study. In order to check whether this effect is really connected with the temperature at which the sample is prepared, we annealed part of the sample 1 at 950°C for 6 h. In Fig. 1 the diffraction pattern for this sample is also presented. It is clearly seen that the diffraction peaks in the annealed sample are broader than in the original sample 1 and they are very similar to the ones in samples 2 and 3.

Examining the crystal structure of BaPbO_3 , we have not found any evidence for monoclinic distortions, accordingly the orthorhombic ($Ibmm$) symmetry was assumed with unit cell parameters $a = 6.0204(30)$, $b = 6.0628(15)$ and $c = 8.5014(15)\text{\AA}$, which agree well with those given by Marx *et al* [12].

III. EXPERIMENTAL

The $^{135}/^{137}\text{Ba}$ spin-echo NQR experiments were performed at 4.2 and 77 K on a phase-coherent spectrometer with an averaging technique and the complex Fourier transformation. We studied the resonance in zero external magnetic field in the frequency region 10–25 MHz. The NQR spectra were measured recording point by point the maximal amplitude of the Fourier transform of the echo signal varying the transmitter frequency. The accuracy of the amplitude measurements was $\sim 10\%$. The weight of the samples we used was about 10 g. The only exception was the sample 3 with the weight about 5 g. The natural abundances of ^{135}Ba and ^{137}Ba are 6.59% and 11.32%, respectively. The signal to noise ratio for the quadrupole resonance is extremely small, therefore relatively large averaging and the Carr-Purcell pulse sequence [13] were employed.

The NQR spectra of barium in BaBiO_3 (sample 1) and BaPbO_3 at $T = 4.2$ K are displayed in Fig. 2. Two peaks in the spectrum of BaBiO_3 correspond to resonance on ^{135}Ba and ^{137}Ba nuclei. The ratio of frequencies, $\nu(^{137}\text{Ba})/\nu(^{135}\text{Ba}) = 1.54$, agrees well with the ratio of the quadrupole moments $Q(^{137}\text{Ba})/Q(^{135}\text{Ba}) = 1.556$. For BaPbO_3 the line near 13 MHz was attributed to the

^{137}Ba nuclei. This assignment was substantiated by an absence of any resonance near 20 MHz, which is expected if the 13 MHz line would correspond to the ^{135}Ba . Note that NQR of ^{137}Ba at the same frequency region was observed recently [14] in $\text{BaPb}_x\text{Bi}_{1-x}\text{O}_3$ ($x=0.91, 0.64$).




FIG. 2. NQR spectra on Ba nuclei in BaBiO_3 (sample 1) and BaPbO_3 taken at $T = 4.2$ K.

The NQR spectra of ^{137}Ba in four BaBiO_3 samples at $T = 4.2$ K, after the correction of the spin-echo amplitude for the weight of the samples, are presented in Fig. 3. All spectra are centered near 18 MHz. The linewidth is ~ 1.2 MHz for the samples 1, 2 while it is ~ 1.7 MHz for the samples 3 and 4. The striking feature of the present study is that the NQR spectra for the samples which belong to group I and group II are similar. As will be shown below, all these spectra correspond to an ordered arrangement of $\text{Bi}^{(4+\delta)+}$ and $\text{Bi}^{(4-\delta)+}$ cations. Therefore the NQR data do not confirm the picture suggested by Chaillout *et al.* (see Section I). The only difference between the group I and group II, which may be found in the spectra presented in Fig. 3, is that the integrated intensity, which is proportional to the number of the resonating nuclei, is approximately two times larger in the sample 1 than the integrated intensity in the three other samples.

Nuclear spin-lattice and spin-spin relaxation times are similar for all compounds: $T_1 \simeq 3.4$ s and $T_2 \simeq 0.6$ ms. Therefore the relaxation can not be responsible for the difference of the spin-echo amplitudes for the sample 1 and samples 2-4. In order to substantiate further the effect, the measurements on the samples 1 and 4 at $T = 77$ K were performed. Note that due to the more suitable set of the relaxation times ($T_1 \simeq 0.04$ s, $T_2 \simeq 0.6$ ms) we

were able to use experimental conditions at which the amplitude of the two-pulse spin echo is practically not influenced by the relaxation. The ratio of areas under the resonance lines was found to be in this case $S_1/S_4 \simeq 1.9$ in a good agreement with the data obtained at 4.2 K.




FIG. 3. ^{137}Ba NQR spectra at $T = 4.2$ K in four BaBiO_3 samples prepared in different ways. The amplitudes are corrected for the weight of the samples. The integrated intensity for the sample 1 is approximately two times larger than for samples 2-4.

IV. DISCUSSION

In the perovskites BaBiO_3 and BaPbO_3 barium occupies the cavities between the Bi(Pb)-O octahedra which form three-dimensional network. Such arrangement implies covalency in the Bi(Pb)-O bonds, while for barium the ionic state Ba^{2+} with filled electronic shells seems to be appropriate approximation. Ionicity of the Ba^{2+} bonding in the perovskite lattice is supported by NMR studies of ^{137}Ba in BaTiO_3 [15], where no chemical shift within the experimental error was found, and also by NMR in $\text{BaPb}_x\text{Bi}_{1-x}\text{O}_3$ [14]. This is further supported by recent pseudopotential calculation of the electronic structure of Ba(B,B')O_3 perovskites, performed by Burton and Cockayne [16].

Thus, when analyzing the EFG at the Ba sites, only the contribution which arises from the charge distribution of the surrounding ions has to be considered. In a conventional point charge model the component V_{ij} of the EFG tensor is given by

$$V_{ij} = (1 - \gamma_\infty) \sum_k e_k (3x_{ik}x_{jk} - \delta_{ij}r_k^2) r_k^{-5}, \quad (1)$$

where γ_∞ is the Sternheimer antishielding factor, e_k is the charge and x_{ik}, x_{jk} are the Cartesian coordinates of the k th ion with a distance r_k from the origin located at a given site. For ^{137}Ba ($I=3/2$) the NQR frequency may be written as

$$\nu = \frac{eQV_{zz}}{2h} \sqrt{1 + \eta^2/3}, \quad (2)$$

where $Q(^{137}\text{Ba}) = +0.28$ b, $\eta = (V_{xx} - V_{yy})/V_{zz}$ is the asymmetry parameter.

In the structure of BaMO_3 ($M=\text{Bi, Pb}$) the symmetry of arrangement of the M ions with respect to Ba sites is almost cubic. Consequently, if the charge distribution is regular, the contributions of the M ions to EFG on the Ba sites approximately cancel. This is the case for BaPbO_3 , where the single valence state of Pb is taken for granted, and also for BaBiO_3 if the structure is ordered with respect to the disproportionated $\text{Bi}^{(4+\delta)+}$ and $\text{Bi}^{(4-\delta)+}$ cations. Note that as far as the ^{137}Ba NQR is concerned, the limiting cases of Bi^{4+} cations or ordered Bi^{3+} and Bi^{5+} cations have nearly the same effect. The main contribution to EFG then arises from the oxygen octahedra rotations around the $[110]$ cubic axes, which are known to be the main distortions of both structures relative to an ideal perovskite crystal.

To demonstrate this point we have calculated the NQR frequency as a function of the rotation angle $\phi_{[110]}$ for idealized BaMO_3 perovskite having undistorted octahedra with a single distance r_{M-O} . In the calculations the value of the antishielding factor $\gamma_\infty = -70.7$ for Ba^{2+} , obtained within the framework of the local density approximation [17], was used. This value agrees with the value $\gamma_\infty = -76$ mentioned in Ref. 18. The lattice sums in (1) were calculated taking into account the contributions from lattice sites inside a sphere with radius of $120\text{\AA}$, although the radius of $60\text{\AA}$ was found to be large enough to obtain the EFG tensor within the 2% accuracy.

Shown in Fig. 4 is the calculated NQR frequency as a function of $\phi_{[110]}$ for two values of r_{M-O} corresponding to averaged Bi-O (over two sites) and Pb-O distances. Taking the mean octahedra tilts $\sim 8.3^\circ$ for BaPbO_3 and $\sim 10.2\text{--}10.6^\circ$ for BaBiO_3 ($T=300$ K) [1–3,12] even this simplified model accounts for observed NQR in the two compounds.

The EFG on Ba sites in BaBiO_3 was calculated using crystal data of Thornton *et al.* [2] for $T = 4.2$ and 293 K (see Table II). In this calculation an ordered arrangement of Bi^{3+} and Bi^{5+} ions was assumed. At $T = 4.2$

K we have obtained NQR frequency of 17.2 MHz in a good agreement to the experimental value 18 MHz. The EFG at 293 K was found to be only ~ 0.85 of the value at 4.2 K reflecting the decrease of the average octahedra tilt from $\sim 11.6^\circ$ to $\sim 10.6^\circ$ in the same temperature region. The experimentally observed decrease of the NQR frequency $\nu(77\text{K})/\nu(4.2\text{K}) = 0.96$ is in line with the above tendency. To our knowledge no data about the crystal structure of BaPbO_3 at $T = 4.2$ K exist, therefore the room temperature structure [12] was used for the calculation. The results are given in Table II. Taking into account that the increase of the octahedra tilts with decreasing temperature seems to be appropriate also for this compound [14], one can conclude that point charge model reproduces correctly the measured values of ^{137}Ba NQR frequency.




FIG. 4. The ^{137}Ba NQR frequency as a function of the angle of oxygen octahedra rotation around $[110]$ cubic axes, calculated using eqs. (1), (2). In the insert the NQR frequency as a function of the angle of additional octahedra rotation around $[001]$ axes is plotted. In the calculations the idealized perovskite BaMO_3 structure consisting of undistorted octahedra with the single distance r_{M-O} was used. The results for $r_{M-O} = 2.147$ (dashed curve) and 2.200 Å (solid curve) which correspond to average Bi-O and Pb-O distances at 300 K are shown. The filled circles correspond to the NQR frequency for $\phi_{[110]} = 8.3^\circ$ and 10.4° , which are the average octahedra tilts for BaPbO_3 and BaBiO_3 ($T = 300$ K), respectively.

Let us now consider the structure of BaBiO_3 disordered with respect to disproportionated $\text{Bi}^{(4+\delta)+}$ and $\text{Bi}^{(4-\delta)+}$ cations with δ substantially different from zero. In this case a variety of random charge configurations of Bi with respect to the Ba sites gives rise to a broad distribution of EFG over the crystal. To simulate the situation we calculated the lattice sums (1) for random configurations of e_k . The contributions from Bi sites inside a sphere with radius of $18\text{\AA}$ (~ 300 ions) were taken into account. To obtain a good statistics 10^5 configurations were con-

sidered. Finally, the contribution from oxygen sites was added. The NQR spectra resulting from the above simulation for $\delta=0.5$ and $\delta=1$ together with the one for $\delta=0$ are plotted in Fig. 5. It is seen that the disorder of $\text{Bi}^{(4+\delta)+}$ and $\text{Bi}^{(4-\delta)+}$ cations results in a strong broadening of the NQR spectrum and decreases the amplitude by an order of magnitude.

We now turn back to the experimental spectra of ^{137}Ba in four BaBiO_3 samples presented in Fig. 3. The analysis we performed suggests that the spectra observed in all samples correspond to an ordered arrangement of $\text{Bi}^{(4+\delta)+}$ and $\text{Bi}^{(4-\delta)+}$ cations. Decrease of the number of the nuclei experiencing this ordered arrangement in the samples 2-4 is equivalent to the decrease of the corresponding volume. We can conclude therefore that samples 2-4 are *partially disordered* with respect to the disproportionated $\text{Bi}^{(4+\delta)+}$ and $\text{Bi}^{(4-\delta)+}$ cations. The degree of the disproportionation δ have to be large enough to smear out the NQR from the charge disordered regions (see Fig. 5). In other words, the present NQR data do not support the model in which only small if any charge transfer between the two Bi sites exists. If the difference of Bi valencies is small, only broadening but not a decrease of the integrated intensity of ^{137}Ba NQR is expected. Our conclusion in this point is in accord with the results of neutron diffraction studies. However, we can't accept the model of Chaillout *et al.* [10] (see Section I) for group II, according to which the structure arrangement of Bi ions corresponds to a '*total disorder of Bi^{3+} and Bi^{5+} cations*', as in this case no NQR spectra at around 18 MHz are expected for the samples 2-4. The results of neutron diffraction and NQR may be consistently explained if we assume that there exists a transition from the long-range ordering of $\text{Bi}^{(4+\delta)+}$ and $\text{Bi}^{(4-\delta)+}$ ($\delta \leq 1$) for group I, to short-range ordering with a coherence length smaller than the intrinsic coherence length for neutrons (group II). Such a transition should not lead to any substantial change in the NQR, but it may smear out corresponding extra reflections in the neutron diffraction patterns. The situation could be similar to the one in the mixed-valency perovskite manganites, where inhomogeneous spatial mixture of charge-ordered and charge-disordered microdomains with a size of 20-30 nm was found recently [19]. It is tempting to connect

TABLE II. Electric field gradient on ^{137}Ba nuclei (V_{zz}), asymmetry parameter (η) and NQR frequency (ν_{calc}) calculated using the point charge model together with the experimental values of NQR frequency (ν_{exp}) for BaBiO_3 and BaPbO_3 .

compound	T(K)	$V_{zz}(10^{21}\text{V/m}^2)$	η	$\nu_{calc}(\text{MHz})$	$\nu_{exp}(\text{MHz})$
BaBiO_3	4.2	-4.88	0.48	17.2	18.0
BaBiO_3	300	-4.15	0.54	14.7	-
BaPbO_3	4.2	-	-	-	13.0
BaPbO_3	300	-2.80	0.47	9.84	-

the broadening of the x-ray diffraction peaks (Fig. 1) for the samples 2-4 with spatial distribution of the lattice parameters which results from such inhomogeneous mixture.




FIG. 5. The simulated NQR spectra of ^{137}Ba in $\text{BaBi}_{0.5}^{(4+\delta)+}\text{Bi}_{0.5}^{(4-\delta)+}\text{O}_3$ disordered with respect to Bi ions for three values of δ . The individual contributions to the spectra are broadened by linewidth 1 MHz. The amplitudes are increased in proportion to ν^2 to reproduce the picture which should be observed experimentally.

Another feature of the present NQR study which was not yet discussed is surprisingly large linewidth of NQR in both BaBiO_3 and BaPbO_3 comparing to linewidth expected for a perfectly ordered structure. The ordinary source of the broadening, i.e. the defects (like oxygen vacancies) or impurities is unlikely. For BaBiO_3 the samples 2 and 3 were prepared from the same mixture of the starting materials, but they show substantially different linewidths (~ 1.2 and ~ 1.7 MHz). On the other hand, the samples 1 and 2, produced in different ways and in different laboratories, show identical spectra. Finally, the NQR spectrum of BaPbO_3 is very similar to that obtained for $\text{BaPb}_{0.91}\text{Bi}_{0.09}\text{O}_3$ (Ref. 14) in spite of 9% substitution of Bi for Pb! The strong broadening of NQR suggests an essential local distortions of the perovskite crystal structure for both compounds. Based on the EXAFS analysis, it was proposed recently [20], that in BaBiO_3 local oxygen octahedra rotations have in addition to the [110] component a disordered component about the [001] axis. In our idealized model of the perovskite structure it is easy to estimate that the observed NQR linewidth may result from a disordered rotation of $\sim 3^\circ$ about the [001] axis (see insert in Fig. 4). Note that for the [100] and [010] axes which make the angle 45° with [110] axis, considerably smaller rotation angle

is enough to account for the NQR linewidth.

V. CONCLUSIONS

The NQR of barium was studied in BaBiO₃ and BaPbO₃. The analysis of the NQR data for BaBiO₃ supports the double valence of the Bi ions. Our results indicate that there exists ordering arrangement of Bi^{(4+ δ)+} and Bi^{(4- δ)+} ions for the samples studied, irrespectively of the preparing conditions, in contradiction with the models used until now. We propose that the degree of the ordering is higher in the BaBiO₃ sample synthesized at 800°C than in the ceramic samples and single crystal, which are prepared at 930-1080°C. The broadening of the NQR suggests that the local distortions of the structure are essential in both BaBiO₃ and BaPbO₃ compounds. The point charge model accounts for observed EFG on Ba sites.

ACKNOWLEDGMENTS

Our thanks to V. G. But'ko and A. A. Gusev for calculation the antishielding factor for Ba²⁺ ion.

This work was supported in part by INTAS grant No 97-1371.

-
- [1] D. E. Cox and A. W. Sleight, Solid State Commun. **19**, 969 (1976).
 - [2] G. Thornton and A. J. Jacobson, Acta Crystallogr. B **34**, 351 (1978).
 - [3] S. Pei, J. D. Jorgensen, B. Dabrowski, D. G. Hinks, D. R. Richards, A. W. Mitchell, J. M. Newsam, S. K. Sinha, D. Vaknin, and A. J. Jacobson, Phys. Rev. B **41**, 4126 (1990).
 - [4] A. Balzarotti, A. P. Menushenkov, N. Motta, and J. Purnans, Solid State Commun. **49**, 887 (1984).
 - [5] S. Tajima, S. Uchida, A. Masaki, H. Takagi, K. Kitazawa, S. Tanaka, and S. Sugai, Phys. Rev. B **35**, 696 (1987).
 - [6] L. F. Mattheiss and D. R. Hamann, Phys. Rev. B **28**, 4227 (1983).
 - [7] X. Zhang and C. R. A. Catlow, Physica C **173**, 25 (1991).
 - [8] M. Nagoshi, T. Suzuki, Y. Fukuda, K. Ueki, A. Tokiwa, K. Kikuchi, Y. Syono, and M. Tachiki, J. Phys.: Condens. Matter **4**, 5769 (1992).
 - [9] Z. N. Akhtar, M. J. Akhtar, and C. R. A. Catlow, J. Phys.: Condens. Matter **5**, 2643 (1992).
 - [10] C. Chaillout, A. Santoro, J. P. Remeika, A. S. Cooper, and G. P. Espinosa, Solid State Commun. **65**, 1363 (1988).
 - [11] L. Reven, J. Shore, S. Yang, T. Duncan, D. Schwartz, J. Chung, and E. Oldfield, Phys. Rev. B **43**, 10 466 (1991).
 - [12] D. T. Marx, P. G. Radaelli, J. D. Jorgensen, R. L. Hitterman, D. G. Hinks, S. Pei, and B. Dabrowski, Phys. Rev. B **46**, 1144 (1992).
 - [13] J. Englich, P. Novák, and H. Lütgemeier, Int. J. Mod. Phys. B **12**, 609 (1998).
 - [14] K. Kumagai, Yu. V. Piskunov, A. Yu. Yakubovskii, S. V. Verkhovskii, A. P. Gerashenko, Yu. I. Zhdanov, K. N. Mikhalev, I. V. Sagaradze, Eu. Yu. Medvedev, S. M. Cheshnitskii, and R. N. Pletnev, Physica C **274**, 209 (1997).
 - [15] T. J. Bastow, J. Phys.: Condens. Matter **1**, 4985 (1989).
 - [16] B. P. Burton and E. Cockayne, Phys. Rev. B **60**, R12 542 (1999).
 - [17] A. A. Gusev, I. M. Reznik, and V. A. Tsitrin, J. Phys.: Condens. Matter **7**, 4855 (1995).
 - [18] R. Sommer, M. Maclione, and J. J. Van der Klink, Ferroelectrics **107**, 307 (1990).
 - [19] S. Mori, C. H. Chen, and S-W. Cheong, Phys. Rev. Lett. **81**, 3972 (1998).
 - [20] Y. Yacoby, S. M. Heald and E. A. Stern, Solid State Commun. **101**, 801 (1997).